

**RENOLIT ALKORPLAN 02339**  
Black geomembrane  
UV Resistant



→ **PRODUCT**

- Black homogenous geomembrane made of flexible polyvinyl chloride (PVC-P).
- Designed for hydraulics works.
- High UV stability (please contact our technical service for required thickness and installation conditions in relation to the geographical location).

→ **CHARACTERISTICS**

- The quality system is certified according to EN ISO 9001 and ISO 14001.
- Resistant to swelling, rotting and ageing.
- Geomembrane produced with high quality resins, this guarantees high consistency of properties and optimum durability.
- Mechanical properties in accordance with EN 13361, 13362, 13492 and EN 13493.
- Very high level of water tightness, even with permanent deformation.
- Large capacity for adaptation to irregularities or deformation of support owing to its high deformability and welding strength.
- High resistance to puncturing.
- Root resistance in accordance with EN 14416.
- Not resistant to bitumen, oil and tar.

→ **INSTALLATION**

- Hot air or hot wedge welding achieves assembly of the geomembrane or prefabricated panels. The weld ability and the quality of the welding done on site can be influenced by atmospheric conditions (temperature, humidity of the air) and also by the state of the surface of the geomembrane (clean surface, more or less wetness of the surface) and must be adapted accordingly.
- Generally when laying gravely sand, gravel, selected fill or concrete on a geomembrane, a geotextile or a protection membrane of non-reinforced PVC-P RENOLIT ALKORPLAN 35020 (protection against dynamic puncturing) should be placed in between. The geomembrane can be used on a bituminous support after the insertion of a suitable separation layer.

## RENOLIT ALKORPLAN 02339

Black geomembrane  
UV Resistant

→ CHARACTERISTICS	NORMS	UNITS	SPECIFICATIONS		
Thickness	EN 1849-2	mm	1.00 +-5%	1.20 +-5%	1.50 +-5%
Density	EN ISO 1183 ASTM D 792	g/cm <sup>3</sup>	1.24 +-5%		
Tensile strength	EN ISO 527	N/mm <sup>2</sup>	≥ 15.5		
Elongation at failure	EN ISO 527	%	≥ 250		
Static puncture resistance (CBR)	EN 12236	kN	1.50 +-10%	1.80 +-10%	2.30 +-10%
Tear strength	ISO 34	kN/m	≥ 40		
Resistant under water pressure	DIN 16726		Waterproof at 6 bar/72 h		
Biaxial deformation	P 84-503		Without rupture		
Dimensional stability after accelerated ageing (6h/80°C)	EN ISO 1107-2	%	≤ 2		
Behaviour after long-term ageing 56d/50°C. Methods A&B.					
- General appearance			No blister		
- Dimensional stability, L&T	EN 14415	%	≤ 2		
- Variation of tensile strength, L&T		%	< ±10		
- Variation of elongation at failure, L&T		%	< ±10		
Folding at a temperature of - 20°C			No cracks at -20°C		
Water permeability	EN 14150	m <sup>3</sup> /m <sup>2</sup> /day	10 <sup>-6</sup>		
Oxidation resistance 90d/85°C	EN 14575		Fulfilled (< 15%)		
Stress cracking resistance	ASTM D5397-99		Not relevant		
Cold folding resistance	EN 495-5		No cracks at -20°C		
Root resistance	EN 14416		Fulfilled		

We reserve the right to amend or change specifications as and when required.

We will be pleased to advise current specifications upon request.

Other technical characteristics are available upon request.

### → STORAGE

- Store in a dry unheated space. Rolls to be parallel and in original packing. Do not stack in cross form or under pressure. The storage area must be of such a nature as not to damage the geomembrane.
- Available width considering the thickness

THICKNESS	WIDTH
1,0 mm	2,10 m
1,2 mm	2,15 m
1,5 mm	2,15 m