




## Technical Data sheet

### RENOLIT ECO RAINBOW COLLECTION ECO OPAQUE LASER



#### Product overview | Produktübersicht | Lista de productos:

Article code <i>Artikelnummer</i> Referencia	Colour <i>Farbe</i> Color	Colour number <i>Farbnummer</i> Número de color			
S10.86.00.0001.000	ECO DOTP OPAQUE LASER WHITE H73	FC06604	300	1400	65
S10.86.00.0002.000	ECO DOTP OPAQUE LASER BLACK H73	FC02002	300	1400	65

#### Technical properties | Technische Eigenschaften | Propiedades técnicas:

Properties <i>Eigenschaften</i> Propiedades	Standard <i>Norm</i> Normativa	Units <i>Einheiten</i> Unidades		LASER 300 µm
Thickness <i>Dicke</i> Espesor	EN 1849-2 [Micrometer]	µ		300 +/-5%
Tensile strength <i>Zugfestigkeit</i> Resistencia a la Tracción	EN ISO 527 - 3 [200 mm/min]	MPA	MD*	>23
			TD*	>20
Elongation at break <i>Reißdehnung</i> Alargamiento en la rotura	EN ISO 527 - 3 [200 mm/min]	%	MD*	>250
			TD*	>250
Shrinkage <i>Schrumpf</i> Contracción	DIN 53377 [10 min.; + 80 °C]	%		<-2,5
Hardness <i>Härte</i> Dureza	EN ISO 868 [6 Sec. Shore D]	-		37 +/-4
Brittleness Temperature <i>Kältebruch-temperatur</i> Temp. de Resistencia al frio	DIN EN 1876-2	°C		0

\* MD: longitudinal, längs, longitudinal  
\* TD: transverse, quer, transversal

