


# RENOLIT ALKORPLUS<sup>81057</sup>

## Double-sided butyl adhesive tape



### PRODUCT DESCRIPTION

Double-sided butyl adhesive tape consisting of a butyl rubber adhesive compound and a peelable liner.

### CHARACTERISTICS

|  | VALUE                | TEST        |
|--|----------------------|-------------|
| Solids   | 100 %                | -           |
| 180° Peel Adhesion                               | 20 N/cm              | ASTM D 1000 |
| 180° Peel Adhesion @ 5°C on concrete             | 17 N/cm              | -           |
| Probe Tack                                       | 8.0 N                | ASTM D 2979 |
| Vertical Flow                                    | 0 mm                 | ISO 7390    |
| Application Temperature Range                    | 0 °C / + 40 °C       | -           |
| Service Temperature Range                        | - 30 °C / + 90 °C    | -           |
| Total Volatile Organic Compound emissions (TVOC) | 30 µg/m <sup>3</sup> | ISO 16000-6 |

### FIELD OF APPLICATION

The **RENOLIT ALKORPLUS<sup>81057</sup>** seam tape is used for jointing **RENOLIT ALKORPLUS** polyethylene vapour control layer overlaps and creating an airtight seal at parapets and around roof penetrations.

### INSTRUCTIONS FOR USE

#### SURFACE PREPARATION

- The surface shall be clean, dry and free from debris, solvent and other surface contamination.

#### USE

For more detailed information regarding correct installation and use please refer to the **RENOLIT** installation instructions.

- Apply the tape onto the surface.
- Press down firmly using a roller or a cloth pad.
- Remove the peelable liner and apply the second surface while avoiding air bubbles.
- Immediately press down firmly using a roller or a cloth pad in order to create an airtight seal.

### PACKAGING

| Type  | Width | Weight   | Roll length | Packaging unit |
|-------|-------|----------|-------------|----------------|
| 81057 | 15 mm | 0,100 kg | 25 m        | 16 rolls / box |

### STORAGE

- Minimum 12 months in original unopened packaging and protected from humidity.
- Store in a well ventilated room and at a maximum temperature of 30°C (storage above 30°C may lead to difficulties to remove the liner when applying).

[WWW.RENOLIT.COM/ROOFING](http://WWW.RENOLIT.COM/ROOFING)

RENOLIT RENOLIT Cramlington Ltd, Station Road - Cramlington, Northumberland NE23 8AQ - United Kingdom  
T +44 1670 718283 - F +44 1670 590096 - [renolit.cramlington@renolit.com](mailto:renolit.cramlington@renolit.com)

RENOLIT Belgium N.V. - Export Dpt. - Industriepark De Bruwaan 43 - 9700 Oudenaarde - Belgium  
T +32 (0)55 33 98 51 - F +32 (0)55 31 86 58 - [renolit.belgium@renolit.com](mailto:renolit.belgium@renolit.com)



*Rely on it.*